FIREROL Medium Wall Single Core Unsheathed & Fire Resistant 0.6/1 kV or 1.8/3 kV EN 50264-3-1 (FRL-MW-1SU-PH15/30/FRL-MW-3SU-PH15/30)

A. Conductor B. Insulation

Application

-Used as power and control cable for protected installations inside and outside of rail and transport vehicles, where handling and installation cost are an important factor.
-Used in control, auxillary and main circuit wiring such as cable harnesses, switchboards and control panels, driver desks etc.

Construction

Conductor
Flexible tinned annealed copper wires, stranded as per HD 383 (IEC 60228) class 5

Insulation
Mica tape+LSZH elastomeric compound as defined in EN 50264-1 (EI 106 to EI 109)

Electrical & Mechanical Properties

Nominal Voltage	0.6/1 kV or 1.8/3 kV
Max. Conductor Temperature	90 °C (fixed installation)
Min. Permissible Ambient Temperature	-25 °C/-40 °C (fixed installation)
Bending Radius	Fixed installation: 10 x Overall Diameter (D<12mm); 12 x Overall Diameter (D>12mm) Flexible installation: 20 x Overall Diameter (D<12mm); 25 x Overall Diameter (D>12mm)

Chemical & Environmental Properties

EN 60684-2	No fluorine
EN 50305; EN 60811-2-1	Resistance to mineral oil & fuel oil, acid & alkali
EN 50305	Resistance to ozone

Fire Performance for Rolling Stock Application

EN 50306-2	Hazard levels HL1, HL2/HL3, HL4
DIN 5510-2	Protection level 1/2/3/4
BS 6853	Interior use 1a, 1b, II; Exterior use 1a, 1b, II
NF F 16-101	F0

Fire Performance in General

EN 50265-2-1; IEC 60332-1-2; NF C 32-070 2.1 (C2)	Vertical flame propagation for a single insulated wire or cable
EN 50266-2-4 + EN 50305; IEC 60332-3-24; NF C 32-070 2.2 (C1); VDE 0472 Teil 804	Vertical flame spread of vertically mounted bunched wires or cables
EN 50268-2; IEC 61034-2; NF C 32-073 ; NF C 20-902; NF F 16 101; VDE 0472 Teil 816	Low Smoke Emission
EN 50267-2-1; IEC 60754-1; NF C 32-074; NF C 20-454; VDE 0472 Teil 815	Halogen Free
EN 50267-2-2/3; IEC 60754-2; NF C 32-074; NF C 20-453; VDE 0472 Teil 813	Low Corrosivity (Acidity & Conductivity)
EN 50305; NF X 70-100; NF F 63 808; TM1-04; BS6853	Low Toxicity
NF F 63 808; BS6853; NF F 16 101	Smoke Index
EN50200: 2000	Resistance to fire of unprotected small cable for use in emergency circuits 4 classifications are defined: PH 15,30,60, or 90 mins;

IEC60331-21

The circuit integrity test under fire of cables rated 0.6/1.0kV and below

FRL-MW-1SU-PH15/30 0.6/1 kV

Nominal Cross-Sectional Area	Conductor Diameter (a)	Min. Mean Thickness of Insulation	Overall Diameter		Weight	Max. Conductor Resistance	Min. Insulation Resistance	
			Min.	Max.		20 °C	20 °C	90 °C
mm²	mm	mm	mm	mm	kg/km	Ω/km	MΩ x km	MΩ x km
1.0	1.25	0.6	2.6	3.1	15	20	11.4	0.114
1.5	1.5	0.7	3.0	3.6	24	13.7	11.0	0.110
2.5	1.95	0.7	3.4	4.1	36	8.21	9.1	0.091
4	2.5	0.7	4.0	4.7	54	5.09	7.5	0.075
6	3.0	0.7	4.4	5.3	76	3.39	6.5	0.065
10	3.9	0.7	5.3	6.2	121	1.95	5.2	0.052
16	5.0	0.7	6.3	7.5	184	1.24	4.2	0.042
25	6.4	0.9	8.0	9.4	289	0.795	4.1	0.041
35	7.7	0.9	9.2	10.9	395	0.565	3.5	0.035
50	9.2	1.0	10.8	12.7	563	0.393	3.3	0.033
70	11.0	1.1	12.7	14.9	796	0.277	3.0	0.030
95	12.5	1.1	14.1	16.6	1032	0.210	2.7	0.027
120	14.2	1.2	15.9	18.7	1318	0.164	2.7	0.027
150	15.8	1.4	17.8	20.9	1650	0.132	2.7	0.027
185	17.5	1.6	19.8	23.2	2018	0.108	2.6	0.026
240	20.1	1.7	22.4	26.3	2649	0.0817	2.6	0.026
300	22.5	1.8	24.8	29.1	3291	0.0654	2.4	0.024
400	25.8	2.0	28.3	33.2	3850	0.0495	2.4	0.024

FRL-MW-3SU-PH15/30 1.8/3 kV

Nominal Cross-Sectional Area	Conductor Diameter (a)	Min. Mean Thickness of Insulation	Overall Diameter		Weight	Max. Conductor Resistance	Min. Insulation Resistance	
			Min.	Max.		20 °C	20 °C	90 °C
mm²	mm	mm	mm	mm	kg/km	Ω/km	MΩ x km	MΩ x km
1.5	1.5	2.0	5.5	6.5	56	13.7	21.0	0.210
2.5	1.95	2.0	5.9	7.0	71	8.21	18.0	0.180
4	2.5	2.0	6.4	7.6	90	5.09	15.5	0.155
6	3.0	2.0	69	8.1	114	3.39	13.7	0.137
10	3.9	2.0	7.7	9.1	165	1.95	11.5	0.115
16	5.0	2.0	8.8	10.3	235	1.24	9.5	0.095
25	6.4	2.0	10.1	11.9	320	0.795	7.9	0.079
35	7.7	2.0	11.3	13.3	440	0.565	6.8	0.068
50	9.2	2.0	12.7	14.9	610	0.393	5.9	0.059
70	11.0	2.0	14.4	16.9	850	0.277	5.0	0.050
95	12.5	2.2	16.2	19.0	1110	0.210	4.5	0.045
120	14.2	2.2	17.8	20.9	1400	0.164	4.0	0.040
150	15.8	2.2	19.3	22.6	1710	0.132	3.7	0.037
185	17.5	2.4	21.1	24.7	2110	0.108	3.4	0.034
240	20.1	2.4	23.9	27.8	2750	0.0817	3.0	0.030
300	22.5	2.4	25.8	30.4	3300	0.0654	2.7	0.027
400	25.8	2.6	29.4	34.5	3900	0.0495	2.4	0.024

(a)= For information, indicative only